

报告编号: SZ172506112

第 1 页 共 4 页

检验检测报告

Test Report

产 品 名 称 (Sample Name)	黄梅龙源石膏粉
委 托 单 位 (Applicant)	河南理工大学
检 验 类 别 (Testing Category)	委托检验



深圳天祥质量技术服务有限公司
Intertek Testing Services Shenzhen Ltd.



深圳天祥质量技术服务有限公司

Intertek Testing Services Shenzhen Ltd.

地址: 深圳市龙岗区坂田街道五和大道北 4012 号元征科技工业园 1 号楼 3、4、5 层及 1 楼西侧 半层和 3 号楼整栋 1-5 层
Address: Building 3,4 and 5, Building 1, west side of Yuanzheng Science and Technology Industrial Park, No.4012,
Wuhe Avenue, Bantian Street, Longgang District, Shenzhen



在线验证
Online verification

报告编号: SZ172506112

第 2 页 共 4 页

委托单位	河南理工大学		
地址	河南省焦作市高新区世纪大道 2001 号		
生产单位	黄梅龙源石膏有限公司		
地址	湖北省黄梅县下新镇马鞍村五组		
样品信息		检测 项目	见后续
样品名称	黄梅龙源石膏粉		
产品数量	5 袋		
产品型号	50kg/袋		
*以上信息内容由申请人提供并确认			
样品接收日期	2025-05-26		
样品检测日期	2025-05-26-2025-06-10		
检测依据	GB/T 5484-2024, JC/T 2074-2011, GB/T 17669.5-1999, GB/T 21524-2008		
检测结果	本次委托检验, 所检项目全部符合要求		
补充说明	委托检验仅对来样负责, 不承担其他连带责任		

检测
检测

签 发: 叶朝
授权签字人

签发日期: 2025 年 05 月 26 日



深圳天祥质量技术服务有限公司
Intertek Testing Services Shenzhen Ltd.
地址: 深圳市龙岗区坂田街道五和大道北 4012 号元征科技工业园 1 号楼 3、4、5 层及 1 楼西侧 半层和 3 号楼整栋 1-5 层
Address: Building 3,4 and 5, Building 1, west side of Yuanzheng Science and Technology Industrial Park, No.4012,
Wuhe Avenue, Bantian Street, Longgang District, Shenzhen



在线验证
Online verification

报告编号: SZ172506112

第 3 页 共 4 页

序号	检验项目	检验结果					
		5 份样品测试值					均值
1	附着水 (42~48℃) (%)	0.08	0.12	0.09	0.13	0.08	0.10
2	结晶水 (225~235℃) (%)	0.4	0.34	0.35	0.35	0.36	0.36
3	三氧化硫 (%)	51.57	51.51	51	51.06	51.11	51.25
4	半水亚硫酸钙 (%)	0.03	0.04	0.02	0.04	0.02	0.03
5	三氧化二铝 (%)	0.03	0.06	0.05	0.06	0.05	0.05
6	三氧化二铁 (%)	0.07	0.07	0.11	0.07	0.08	0.08
7	二氧化硅 (%)	0.04	0.07	0.04	0.05	0.05	0.05
8	三氧化二铁 (%)	0.04	0.06	0.05	0.05	0.05	0.05
9	氧化钙 (%)	40.42	39.95	40.34	39.94	40.15	40.16
10	氧化镁 (%)	2.16	2.36	2.35	2.22	2.31	2.28
11	氧化钾 (%)	0.04	0.05	0.03	0.04	0.04	0.04
12	氧化钠 (%)	0.04	0.07	0.07	0.06	0.06	0.06
13	二氧化钛 (%)	0.02	0.02	0.02	0.02	0.02	0.02
14	氯离子 (%)	0.01	0.01	0.01	0.01	0.01	0.01
15	水溶氟离子 (%)	0.009	0.007	0.008	0.008	0.008	0.008
16	pH (50g/L 水溶液, 25℃)	9	8.7	8.7	8.8	8.8	8.8
17	酸不溶物 (%)	1.58	1.23	1.61	1.34	1.49	1.45
18	细度	+0.8mm	0.14	0.1	0.14	0.11	0.13
		0.8~0.4mm	0.1	0.09	0.09	0.08	0.09
		0.4~0.2mm	0.39	0.38	0.32	0.36	0.35
		0.2~0.1mm	1.94	1.86	1.46	1.87	1.73
		<0.1mm	97.43	97.57	97.99	97.58	97.69
19	堆积密度 (g/L)	1047	1108	1109	1070	1081	1083

RVIC.
术服
专用章

报告结束

深圳天祥质量技术服务有限公司

Intertek Testing Services Shenzhen Ltd.

地址: 深圳市龙岗区坂田街道五和大道北 4012 号元征科技工业园 1 号楼 3、4、5 层及 1 楼西侧 半层和 3 号楼整栋 1-5 层

Address: Building 3,4 and 5, Building 1, west side of Yuanzheng Science and Technology Industrial Park, No.4012, Wuhe Avenue, Bantian Street, Longgang District, Shenzhen



在线验证
Online verification

报告编号: SZ172506112

第 4 页 共 4 页

注 意 事 项

Notice Items

1、本报告无批准人签字、报告专用章及骑缝章无效。

This report shall be invalid without the signature of the approver, the special seal for the report and the cross-page seal.

2、本报告不得擅自修改、增加或删除。

This report shall not be modified, added or deleted without authorization.

3、报告结果只对本次受检样品负责。若对检测结果有异议,请在报告签发日期后两天内书面提出,逾期不予受理。

The results of the report are only responsible for the samples tested this time. If there is any objection to the test result, please submit it in writing within fifteen days after the date of issuance of the report. Overdue will not be accepted.

4、未经天祥检测书面同意,不得部分复制本报告,亦不可作为宣传品使用。

Without the written consent of Intertek, this report shall not be partially copied or used as publicity materials.

5、当需要结果符合性评价时,若客户无要求,一般不考虑结果的测量不确定度的影响。

When the result conformity evaluation is required, if the customer does not require it, the influence of the measurement uncertainty of the result is generally not considered.

6、此报告无 CMA 标识时,检测数据仅限科研、教学、内部质量控制或研发等活动使用。

When the report has not CMA logo, the test data is limited to scientific research, teaching, internal quality control or research and development activities.

7、本公司出具纸质正版报告与电子数字签名版具备相同效力,当两者内容有差异时以电子数字签名版为准。The company's paper genuine report has the same legal effect as the electronic digital signature version. When the contents are different, subject to electronic digital signature version.



深圳天祥质量技术服务有限公司

Intertek Testing Services Shenzhen Ltd.

地址: 深圳市龙岗区坂田街道五和大道北 4012 号元征科技工业园 1 号楼 3、4、5 层及 1 楼西侧 半层和 3 号楼整栋 1-5 层

Address: Building 3, 4 and 5, Building 1, west side of Yuanzheng Science and Technology Industrial Park, No. 4012, Wuhe Avenue, Bantian Street, Longgang District, Shenzhen



在线验证
Online verification